

Listing of Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (original) A method for forming a homogeneous mixture of powder organic materials including at least one dopant component and one host component to form a pellet for use in thermal physical vapor deposition to produce an organic layer on a substrate for use in an organic light-emitting device, comprising:
 - a) combining organic materials in a powder form, such materials including at least one dopant component and one host component and placing the powder organic materials in a container;
 - b) heating the container having the powder organic materials in a range of temperatures from 40 to 100°C for 30 to 100 minutes while purging the atmosphere in the container so that the atmosphere has a reduced pressure in a range from 10^{-1} to 10^{-3} Torr to remove moisture from the container atmosphere;
 - c) filling the container with an inert atmosphere;
 - d) mixing the powder organic materials in the inert atmosphere using a mixing mechanism to form a homogeneous mixture of powder organic materials; and
 - e) compacting the homogenous mixture of powder organic materials to form a pellet suitable for thermal physical vaporization to produce an organic layer on a substrate for use in an organic light-emitting device.
2. (original) The method of claim 1 wherein the mixing mechanism includes a propeller or a turbine blade.
3. The method of claim 1 wherein the amount of dopant component varies between 0.1 and 20% by weight of the total weight of the mixture.
4. (original) The method of claim 1 wherein the inert atmosphere includes nitrogen gas, argon gas, or a mixture thereof.
5. (original) The method of claim 1 wherein the homogeneous mixture of powder organic materials is compacted at a pressure in a range of 3,000 to 20,000 pounds per square inch.

6. (original) The method of claim 1 further including storing the container before mixing in a reduced pressure atmosphere in a range from 10^{-1} to 10^{-3} Torr.

7. (original) The method of claim 1 wherein mixing using the mixing mechanism includes rotating the mixing mechanism in a first periodic motion at a rate in a range of 20,000 to 50,000 revolutions per minute.

8. (original) The method of claim 1 wherein mixing includes rotating the container in a second periodic motion at a rate in a range of 10 to 60 revolutions per minute.

9. (Currently Amended) The method of claim 1 wherein mixing using the mixing mechanism includes rotating while reciprocating in the mixing container ~~mechanism in a third periodic motion at a rate in a range of 20 to 60 cycles per minute.~~

10. (Currently amended) The method of claim 9 wherein ~~the third periodic motion of~~ the mixing mechanism includes traversing the length inside of the sealed container by means of a pneumatic cylinder and a traversing bracket.

11. Cancelled.
12. Cancelled.
13. Cancelled.
14. Cancelled.
15. Cancelled.
16. Cancelled.
17. Cancelled.
18. Cancelled.
19. Cancelled.
20. Cancelled.
21. Cancelled.
22. Cancelled.
23. Cancelled.
24. Cancelled.
25. Cancelled.
26. Cancelled.